

Coating thickness
measurement

MiniTest 70 Series

MiniTest 70F/70FN



Versatile coating thickness gauges

- for fast and precise measurements of
 - non-magnetic coatings on steel
0 ... 3000 µm
 - insulating coatings on non-ferrous metals
0 ... 2500 µm
- automatic identification of the substrate material
- built-in sensor
- proven measuring methods
- statistics function

MiniTest 70 - Pocket-sized Coating Thickness Gauge

Application

Designed for quick and easy non-destructive coating thickness measurement, the MiniTest 70 series is available in two models:

- MiniTest 70F with built-in sensor for measuring non-magnetic coatings applied on steel
- MiniTest 70FN with a built-in dual sensor for measuring non-magnetic coatings applied on steel and insulating coatings on non-ferrous metals.

Description

The MiniTest 70 Series are compact, pocket sized coating thickness testing gauges. The simple 4-button operation, clear display and built-in statistics displaying the number of readings taken, the minimum, maximum, mean values and standard deviation makes the MiniTest 70 Series ideal for on-site applications. With new simplified operation, no special training is required to operate these gauges. An audible signal confirms reading acquisition. The MiniTest 70 Series are powered by a standard single AA battery and when the battery gets low, a BAT symbol appears to indicate that the battery needs to be changed.

Special feature of the MiniTest 70FN model: It incorporates a dual sensor for automatic identification of the substrate material. The gauge upon contact with the surface automatically switches to the suitable measuring principle based on your application: magnetic-induction or eddy currents.

Scope of delivery

- MiniTest 70 F or MiniTest 70 FN
- Steel test plate (for model 70 F)
- Steel and aluminium test plates (for model 70 FN)
- Calibration foils
- Operating instructions
- Gauge tether
- Storage case

MODEL	MiniTest 70 F	MiniTest 70 FN
Properties		
Measuring range	0...3 mm/120 mils	F: 0...3 mm/120 mils / N: 0...2.5 mm/100 mils
Measuring principle	magnetic-induction	magnetic-induction/eddy currents
Signal processing	Sensor integrated 32-bit signal processing (SIDSP ¹)	
Accuracy ¹	$\pm (1.5 \mu\text{m} + 3\% \text{ of reading})$ with 1-point calibration $\pm (0.06 \text{ mils} + 3\% \text{ of reading})$ with 1-point calibration $\pm (1.5 \mu\text{m} + 2\% \text{ of reading})$ with 2-point calibration ² $\pm (0.06 \text{ mils} + 2\% \text{ of reading})$ with 2-point calibration ²	
Repeatability ¹	$\pm (1 \mu\text{m} + 1\% \text{ of reading}) / \pm (0.04 \text{ mils} + 1\% \text{ of reading})$	
Low range resolution	0.5 μm ; 0.02 mils	
Minimum curvature radius convex	5 mm; 0.2"	
Minimum curvature radius concave	40 mm; 1.60"	
Minimum substrate thickness	F: 0.5 mm; 0.02" / N: 0.04 mm; 0.0016"	
Measuring units	metric/imperial switchable	
Calibration modes	1-point calibration, 2-point calibration	
Statistics	n, x, s, Min, Max	
Operating temperature range	-10°C...+60°C; 14°F...140°F	
Storage temperature range	-20°C...+70°C; -4°F...158°F	
Power supply	1x AA (Mignon)-battery	
International standards	DIN EN ISO 1461, 2064, 2178, 2360, 2808, 3882, ASTM B 244, B 499, D7091, E 376	
Dimensions	approx. 157 mm length, Ø 27 mm; 5.2" length, Ø 1.06"	
Weight incl. battery	approx. 80 g, 2.8 oz	

¹ according to DIN 55350 Part 13

² with calibration close to the thickness to be expected and related to ElektroPhysik calibration standards

ElektroPhysik
 Pasteurstr. 15
 D-50735 Köln
 Tel.: +49 (0) 221 7 52 04-0
 Fax: +49 (0) 221 7 52 04-67
 www.elektrophysik.com
 info@elektrophysik.com

ElektroPhysik USA
 778 West Algonquin Rd.
 Arlington Heights IL 60005
 Phone: +1 847 4 37-6616
 Fax: +1 847 4 37-00 53
 www.elektrophysik.com
 epusa@elektrophysik.com

ElektroPhysik Nederland
 Borgharenweg 140
 6222 AA Maastricht
 Tel.: +31(0)43/3 52 00 60
 Fax: +31(0)43/3 6311 68
 www.elektrophysik.com
 epnl@elektrophysik.com

ElektroPhysik

